



## Nova Universal Eco-2 Developer

*Developer for Thermal and CTcP-UV positive plates*

Developer for Thermal and CTcP-UV positive plates. Ready to use developer.

### Properties

- **DURABILITY:** Its specific formulation permits high productivity in square meters developed.
- **CLEANING:** Its dissolution capability reduces the accumulation of emulsion in the filters, rollers and bath tank, keeping them cleaner.
- **COMPATIBILITY:** Capable to develop the major positive Thermal CTP (except closed systems) and CTcP UV plates.
- Non-aggressive to the anodizing layer of the plates.
- With buffered agents to minimize the aggression to the image area.
- It contains corrosion inhibitors.
- Conductivity: 83-87 mS (at 25°C).

### How to use \*

PLATE	WORKING TEMPERATURE	DEVELOPING TIME
Nova Aventus	23 ± 1°C	25± 5 sec.

DEVELOPER	TOP UP RATES
Replenishment rate	100 - 120 ml/m <sup>2</sup>
Anti-ox Standby ON	120 - 140 ml/h
Anti-ox Standby OFF	120 - 140 ml/h

\* These values may vary depending on the conditions and type of the processor.

### Packaging

20 liters. (Other packaging available under request).

Nova **Universal Eco-2**

**AtéCe'**  
GRAPHIC PRODUCTS

 **ECO CHEMISTRY**